



Product Specification
Pipelines & Fittings
DENSO PENETRATING PRIMER

DESCRIPTION: A bitumen based primer for all iron or steel surfaces prior to the application of Denso Ultraseal Tape as part of the Steelcoat 400 System. It allows repositioning of the tape during application whilst developing a strong permanent bond to wire brushed surfaces.

COMPOSITION: Butyl and latex resin blend.

PROPERTIES:

Specific Gravity:	0.9
Covering Capacity:	9-11m ² /litre
Wet Film Thickness:	90 - 110 micron
Dry Film Thickness:	45 - 55 micron
Drying Time:	30 minutes
Flash Point:	32°c minimum
Application Temperature Range:	0°c to 55°c

SURFACE PREPARATION:

Surfaces must be clean and dry and free from loose rust, scale and non-adherent coatings. Surfaces should be grit blasted, water blasted or well wire brush to St2.